

Technisches Datenblatt

Artikel: Daytona

Test method		Nominal value	Real value
Colour Fastnes to rubbing (Graumaßstab Stufe 1-5)	DIN EN ISO 11640		
50 Tours dry		> 3	5
50 Tours wet		> 3	4
20 Tours		> 3	4
Colour fastness to light	IUF402	> 3	> 3/4
Tear strength (N/mm)	DIN EN ISO 3377-1/2	> 24	57,5
Flexing endurance, dry (20.000 bucklings)	IUP/20Keine Tears	No Tears	No Tears

Date: 01/21/2013

We point out hat this specification sheet does not substitute the customer's quality control and obligation to inspect the delivered goods. These values are not a warranty in legal sense.

